



# KÖSTER CT 127 1C Silane Primer

**Technical Data Sheet CT 127 005** 

Issued: 2019-09-09

# One-component, flexible, UV and weather-stable, solvent-free, transparent primer for light to medium mechanical loads and sealing coat for broadcast KÖSTER CT 227 1C Silane

# **Features**

KÖSTER CT 127 one component Silane Primer is a UV and weatherstable, flexible, solvent-free, transparent primer and topcoat for light to medium mechanical loads.

# **Technical Data**

Consistency approx. 100 mPa·s (+ 23 °C) Density approx. 1.0 g/m $^2$  Color transparent Application temperature min. + 5 °C Pot life (+ 23 °C) approx. 1 hour

# **Fields of Application**

Primer for KÖSTER CT 227 1C Silane, as well as a top coat for coating systems in which KÖSTER CT 227 1C Silan is broadcast with KÖSTER Color Chips or other broadcast materials. Due to the very good UV resistance, the material can be used indoors and outdoors.

#### Substrate

The substrates to be sealed must be solid, free of dust, oil and grease, and other adhesion inhibiting compounds. Sanding, dusty, or soiled surfaces are to be removed by milling and / or shot blasting down to a coatable, clean substrate. The minimum bond strength of the substrate must be 1.5 N / mm² and may have a maximum residual moisture content of 4 M%. As primer, KÖSTER CT 127 1C Silane Primer is applied in a single layer rolled in two directions. Once the primer has hardened, KÖSTER CT 227 1C Silane is installed.

# **Application**

The material is processed with a brush or a short-napped roller. As a rule, a single cross rolled layer is sufficient. The consumption as a primer is 0.4 - 0.5 kg / m². In the case of broadcasting with KÖSTER Color Chips, the chips are covered with a layer of KÖSTER 127 1C Silane Primer. The consumption is 0.1 kg / m². When using kiln-dried quartz sand as a broadcast, the consumption depends on the grain size and is between approx. 0.5 - 0.8 kg / m².

The room temperature must be at least +3 ° C above the dew point during processing and for at least four hours after processing, (see dew point table).

# Consumption

 $400\text{-}500~\text{g/m}^2$  as primer,  $100\text{-}800~\text{g/m}^2$  as finish coat, depending on the broadcast

# Cleaning

Clean tools immediately after use with KÖSTER Universal Cleaner.

# Packaging

CT 127 005 5 kg jerrycan

# Storage

Store cool but frost free between + 5  $^{\circ}$ C and + 25  $^{\circ}$ C. In originally sealed packages it can be stored for a minimum of 6 months. The container should be stored turned on it's lid to prevent moisture from entering.

#### Safety

Wear protective gloves and goggles when processing the material. Observe all governmental, state, and local safety regulations while processing the material.

#### Related products

KÖSTER CT 227 1C Silane Prod. code CT 227
KÖSTER Color-Chips Prod. code CT 429
KÖSTER Resin Roller 250 mm Prod. code CT 916
KÖSTER Resin Roller 150 mm Prod. code CT 917
KÖSTER Universal Cleaner Prod. code X 910 010
KÖSTER Rubber Gloves Prod. code X 920 001

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustment to the recommendations given here for standard cases. Specifications made by our employees representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER CT 127 1C Silane Primer